

TECHNICAL DATA SHEET

KARNAKYD – 3270

Long Oil Alkyd

Long oil alkyd based on Pentaerythritol and Dehydrated Castor Oil

PRINCIPAL PROPERTIES

- High Gloss
- Excellent adhesion
- Very good flow

APPLICATIONS

It is used in low cost coloured enamel

PRODUCT SPECIFICATIONS

PARAMETERS	SPECIFICATIONS
Type of oil	Dehydrated castor oil
Oil length	65
Acid value on solid	<12 mg KOH /gm
Viscosity 50% solid in MTO	100-120 seconds B-4 @30 C
Colour on gardener scale	6.0 Max.
Clarity	Clear
Non-volatile content	70+ _2%
Surface dry	4-5 Hours
Hard dry	12 Hours

