

Micaceous Iron Oxide | Product description and uses

KPPL Micaceous Iron Oxide is a high quality, high build, protective finish based on special resins and Micaceous Iron Oxide pigment, designed for the protection of exposed structural steel Work and general metal surfaces. It is ideal for use on bridges, pylons, storage tanks, galvanized roofing sheets etc. It has exceptional flexibility, is durable and easy to apply.

Surface Preparation	Surfaces must be thoroughly cleaned before application of paint. Remove rust and mill scale by scraping and wire brushing. Prime with the appropriate metal primer and finish off with 2- 3 coats of Micaceous Iron Oxide finish.
Finish	Metallic Matt.
Application	By brush or spray.
Thinning and mixing	KPPL Thinner or White Spirit
Equipment cleaning	White Spirit
Drying Time	Touch dry: 2 - 4 hours. Through dry: 24 hours
Colour Range	Silver Grey, Metallic Blue and Metallic Green.
Spreading Capacity	10-12m2 Per Litre.
Pack Sizes	4 Litres and 20 Litres.
Hazard symbols	Highly Flammable, Toxic, Harmful to the environment