

## The Colours of Corrosion Protection

### TECHNICAL DATA SHEET

## Specialty Polyester Resin

**K- 7075 (70/30)**

### General Information:

K-7075 is a carboxylated polyester resin designed for hybrid system. It is used with Epoxy resin at the ratio 70:30. This gives a very good flow with good over baking resistance and mechanical properties. It is used in matt finish as well as in structure finish

### Product Specification:

1. Appearance	Solid granules.
2. Colour	Slight yellower.
3. Acid value (mg.KOH/gm.)	32-36.
4. Glass transition temp. (TG.) °C	59 °C
5. Viscosity @200 °C	55-65 °C

### Stating formulation: (Glossy White, Powder coating)

Component	Weight
K – 7075	420
Epoxy resin	180
Titanium dioxide (R)	170
Blanc Fix ( filler)	216
Flow control agent	10
Benzoin	4



## The Colours of Corrosion Protection

### TECHNICAL DATA SHEET

#### APPLICATION PROPERTIES: -

- |                                   |   |
|-----------------------------------|---|
| 1) Baking schedule                | : 180 °C – 10 min. (Metal Temperature)<br>In air circulated oven. |
| 2) Film Thickness                 | : 50 – 60 microns   |
| 3) Gloss at 60 deg. @             | : >95 unit  |
| 4) Mechanical (a) Reverse impacts | : 120 kg-cm.minimum   |
| (b) Direct impacts                | : 120 kg-cm.minimum   |
| 5) Bend Test (Ø 2 mm)             | : Passes  |
| 6) Over bake Resistance           | : Passes  |

#### STORAGE:

Keep away from heat source & direct sunlight. Avoid temp.more than 30 degree C.

#### PACKING;

25 kg. Net in paper bag with **LDPE** bag.

Data given above are based on laboratory tests; the suitability of the product has to be tested in each case. KPPL retains the right to change the qualifications at any time without any announcement and notification. It is the user's responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of result is extended since conditions of use are beyond our control.

