

TECHNICAL DATA SHEET

**OIL FREE SATURATED POLYESTER SUPERDURABLE
RESIN**

Top Coat Resin

KP - 5065

Type: Oil free saturated polyester resin

Form of delivery: 65 % in solvent C-9/ Butyl glycol (4:1)

General Information:

KP – 5065 is linear oil free polyester super durable resin developed for use in coil coating, sheet fed metal decorating and general industrial applications. KP-5065 is engineered for high performance and good exterior durability and high performance.

Features

KP-6065 is engineered for severe exterior building product applications. High weatherability, Good formability, Excellent weathering performance, materials for buildings.

Product Specification:

1. Appearance	: Clear transparent viscous liquid
2. Colour	: Pale yellow to water white
3. Acid value (mg.KOH/gm.)	: 0-5 Max.
4. Non volatile matter 1 hr @ 150 °C	: 65 ± 2 %
5. Viscosity @25 °C (4/20 RPM) B.Field	: 3500 -40000 Cps
6. Hydroxyl value	: 40 – 45 mgKOH/g
7. Specific gravity	: 1.08 ± 0.02
8. Molecular wt.(mn)	: approx.3000



TECHNICAL DATA SHEET

KP-5065 is usually cross linked with HMM Melamine resins. The addition of HMMM is usually between 15 – 30% on solid basis. Incorporation of acid catalyst e.g. Para toluene sulphonic acid promotes the curing. 1% to 5% of acid catalyst on Melamine solids is recommended.

The product has excellent pigment wetting properties and high yield pigment concentrates can be formulated.

CURING SCHEDULES:

Coil Coating finishes based on KP-4060 can be cured using a peak metal temperature of 232°C - 240°C. For Metal Decorating, a cure schedule of 10 minutes at 160 -200°C depending on requirements is recommended; cure response will increase with temperature, but flexibility may be reduced with high levels of catalyst. For General Industrial applications a baking schedule of 30 minutes at 150°C will be suitable.	Metal Decorating: 72 : 18 : 10 KP-4060 Curing of 10 minutes at 160 - 200 is recommended. Aromatic hydrocarbons are recommended.
	General Industrial enamels: 70 : 30 to 80 : 20 on solids with hexamethoxymethyl melamine resin or partly methylated melamine with 2% PTSA catalyst on amino levels. Baking of 30 minutes at 150 C is recommended. Blend of aromatic hydrocarbon/ alcohol are suggested

STORAGE:

Keep away from heat source & direct sunlight. Avoid temp.more than 30 degree C.

PACKING;

210 kg. Net in new MS drums

Data given above are based on laboratory tests; the suitability of the product has to be tested in each case. KPPL retains the right to change the qualifications at any time without any announcement and notification. It is the user's responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of result is extended since conditions of use are beyond our control.

